



VALPAINT S.p.A.  
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY  
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384  
E-mail: info@valpaint.it  
C.F./P.IVA/R.I. di AN 01108220425  
Capitale Sociale € 500.000,00 i.v.

www.valpaint.it • www.valpaintjungle.it

SC 00245

## MAGIC LIGHT FINITURA K 100

### Technical Scheet

**NAME:**

**MAGIC LIGHT FINITURA K 100**

**TYPE:**

Water –based luminescent finish

**USE:**

To be added to decorative paints, transparent waterbased resins, breathable and washable finishes.

**CHARACTERISTICS:**

**specific weight :** 1.050 ± 30 gr/LT at 25°C

**viscosity:** = = =

**yield:** 6-7 m<sup>2</sup>/LT one coating on smooth surfaces (it may vary according to the roughness, porosity and surface absorption and to the method of application)

**aesthetic effect:** Luminescent in darkness

**colours:** Blue-green in darkness

**packaging:** LT. 0,250- LT. 1

**DRYING:**

**on the surface:** 2-3 hours at 20°C

**Over-painting:** 6-8 hours at 20°C

**below the surface:** 36-48 hours at 20°C

**CHARACTERISTICS AND RESISTENCE:**

transparent water-based paint for indoor use that absorbs both natural and artificial light before returning it in complete darkness.

This is precisely why, by lighting a room decorated with MAGIC LIGHT for 5 minutes, when the lights is then switched off, the treated walls will gradually light up again before stabilizing a few minutes later.

Luminescence may last from 6 to 8 hours, depending on the quantity of light absorbed and the intensity of the darkness, reducing gradually over this time. MAGIC LIGHT Finish K100 remains matt and breathable but above all transparent, without altering the underlying colour or effect, particularly on light colours; dark colours may be altered slightly. Therefore, the lighter the colour of the support, the more MAGIC LIGHT Finish K100 will light up in the dark. The illuminating power of MAGIC LIGHT can be strengthened by using Wood-type lamps (neon or purple lamp), to be switched on intermittently for 2 - 3 minutes every 3 - 4 hours.

Always apply one coat of undiluted Finish V 16 using a brush or roller. After approximately 12 hours at 20°C, apply MAGIC LIGHT Finish K100

**PREPARATION OF THE SURFACE**

**PREPARATION OF THE PRODUCT:**

**APPLICATION:**

**thinning:** ready to use – mix well

**APPLICATION CYCLE:**

**system:** roller-pad

**number coating:** 1 or more

Magic Light Finish K 100 can be applied on new and old paints, smooth or rough surfaces but well adhering and not peeling using Roller PV 31 and pad till the product is still wet using Pad PV 33 or Roller PV 30

**Storage:** make sure the tin is tightly closed, even after use, and store at a temperature between +10°C and +30°C.

**Shelf life:** approximately 1 year, if well sealed and never opened

**NOTES:**

Mix well before using with a wooden stick or metallic one

page 1/2



VALPAIN S.p.A.  
Via dell'Industria, 80 - 60020 POLVERIGI (AN) ITALY  
Tel. +39 071 906383 (r.a.) - Fax +39 071 906384  
E-mail: info@valpaint.it  
C.F./P.IVA/R.I. di AN 01108220425  
Capitale Sociale € 500.000,00 i.v.

[www.valpaint.it](http://www.valpaint.it) • [www.valpaintjungle.it](http://www.valpaintjungle.it)

## SC 00245

Application temperature must be not inferior to +5°C and superior to +30°C. Wash the tools soon after use with water and soap.

**Technical sheet n° SC 00245 issued by the Control Quality Manager:**

**Edition n°1**

**April 2014**